


FORMOSA CHEMICALS & FIBRE CORPORATION
TAIRISAN[®] SAN Resin

Property	Unit	Test Method	Test Condition	General Grade
				NF2100
Tensile Strength	kg/cm ² (MPa)	ASTM D-638	23 °C	700 (69)
Flexural Strength	kg/cm ² (MPa)	ASTM D-790	23 °C	1200 (118)
Flexural Modulus	kg/cm ² (MPa)	ASTM D-790	23 °C	35000 (3430)
Rockwell Hardness	R-scale	ASTM D-785	23 °C	M-78
Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256	23 °C 1/4" bar	1.5 (15)
Heat Deflection Temperature	°C	ASTM D-648	Unannealed 18.6 kg/cm ² 1/4" bar	92
Melt Flow Index	g/10 min	ASTM D-1238	200°C × 5kg	5.0
			220°C × 10kg	50
Specific Gravity		ASTM D-792	23°C/23°C	1.06
Flammability		UL-94	FILE NO. E162823	1.5mm HB 3.0mm HB All Color
Characteristics	High flow Injection grade			

All tests were run under laboratory conditions, ASTM, ISO testing procedures. The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 / FAX: +886-2-27131649 /

Address: No.201, Dunhua N. Rd., Songshan Dist., Taipei City 105, Taiwan

Website: <https://en.fcfc-plastics.com/>

